



Expanded bead foam packaging materials

WWW.ARPLANK.COM

Chemical Resistance

Chemical Resistance Information for ARPRO® Expanded Polypropylene (EPP) and ARPAK® Expanded Polyethylene (EPE) Beads

Classification	Chemical Name	Observation / Effect	
		EPP	EPE
Mineral Oil	Lubricating Oil	1	1
	Engine Oil	1	1
	Gasoline	2	2
	Kerosene	2	2
	Heavy Oil	1	1
Organic Solvent	Toluene	2	2
	Benzene	2	2
	Acetone	2	2
	Ethyl Alcohol	1	1
	n-Heptane	2	2
	Carbon Tetrachloride	2	2
	Trichloroethylene	2	2
	Ethyl Acetate	1	1
	Methyl Ethyl Ketone	2	2
	Formaldehyde	1	1
Inorganic	10% Sol. Sulphuric Acid	1	1
	10% Sol. Nitric Acid	1	1
	10% Sol. Hydrochloric Acid	1	2
	10% Sol. Sodium Hydroxide	1	1
	Ammonium Solution	1	1

Key: 1= No Effect
2= Slight Swelling
3= Significant Swelling
4= Dissolved

ARPRO® and ARPAK® are registered trademarks of JSP Licenses, LLC.
PUBLICATION: JSP-ChemicalResistance-EPP&EPE-2006/06

The above data reflects the performance of ARPLANK® panels under controlled test conditions using limited product samples. There can be no assurance that similar results will be achieved in simulated tests or actual commercial use of ARPLANK® panels. JSP makes no representation or warranty, and does not assume any liability, with respect to the accuracy or completeness of such information or the product performance in any particular instance. JSP makes no representation or warranty with respect to ARPLANK® panels, express or implied, including, without limitation, any warranty of merchantability, fitness for a particular purpose, quality or conformity with any description or sample.

ARPRO®
Expanded Polypropylene (EPP)

A PRODUCT OF
JSP
INNOVATION SIMPLIFIED
WWW.JSP.COM